

3600.5825
August 21, 2002 (12:28PM)

#2/P4-a
Docket: AM-5825
8/23/02

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of: Diana Xiaobing MA

Attorneys Docket: AM-5825

Serial No.: 09/922,980

Art Unit No.: 2825

Filed: August 6, 2001

Examiner: R. Rocchegiani

For: "INTEGRATED SYSTEM FOR OXIDE ETCHING AND METAL LINER DEPOSITION"

Commissioner of Patents
Washington, DC 20231

FAX COPY RECEIVED

RESPONSE TO RESTRICTION REQUIREMENT AND
AMENDMENT UNDER 37 CFR §1.115

AUG 21 2002
TECHNOLOGY CENTER 2800

Sir:

In a Preliminary Amendment for consideration before initial examination, please amend the above application as follows:

In the specification:

Two Paragraphs at page 2, line 14 to page 3, line 15:

Conventionally, the inter-level dielectric layers have been oxide layers formed of silica of the approximate composition SiO_2 or related silicate glasses such as borophosphosilicate glass (BPSG). However, these materials have a relatively high dielectric constant k of about 3.9 but even with process variations the value is limited to $k < 4.0$. In view of the increased operating frequencies of advanced integrated circuits and the reduced spacing between conductive features, such as buses, there has been much recent development in low- k inter-level dielectric materials having reduced dielectric constants of less than 3.9. Doped silica such as fluorosilicate glass (FSG) has a dielectric constant of somewhat over 3. Other low- k dielectrics are being developed